

## Specification Sheet

Nylon 12 Granules

(C<sub>12</sub>H<sub>23</sub>NO)<sub>n</sub>, Purity: 99.9%

Stock No: NS6130-12-000925, CAS: 24937-16-4

<b>Product</b>	:	<b>Nylon 12 granules</b>
Stock No	:	NS6130-12-000925
CAS	:	24937-16-4
Purity	:	99.9%
Molecular Formula	:	(C <sub>12</sub> H <sub>23</sub> NO) <sub>n</sub>
Melting Point	:	178-180 °C
Density	:	1.01g/cm <sup>3</sup>
Drying temperature	:	100 °C
Drying time	:	3 ~ 4 hours
Nozzle temperature	:	250 °C
Mold temperature	:	85 ~ 90 °C
Solubility	:	Insoluble in cold water
<b>Main Inspect Verifier</b>	:	<b>Manager QC</b>

**Note:** Product Specification are subject to amendment and may change over time