

# Specification Sheet

Cu, Purity: >99.8%, APS: 10?m

Stock No: NS6130-12-000330, CAS: 7440-50-8

<b>Product</b>	:	<b>Copper Foil</b>
Stock No	:	NS6130-12-000330
CAS	:	7440-50-8
Purity	:	≥99.8%
Thickness	:	10μm (8μm, 9μm, 12μm, 15μm, 20μm)
Tensile Strength	:	≥25 Kg/mm <sup>2</sup>
Surface density	:	95-100g/m <sup>2</sup>
Extensibility	:	≥2.5%
Roughness Rz	:	≤3.0μm
Thickness tolerance	:	-0, +3
Width tolerance	:	±1
Tolerance oxidation susceptibility	:	160□/10min.no oxidation
Joint	:	1Pcs/roll
Roll weight	:	Consulted By Supplier and Acquire
Polished	:	Both Side Polished
Coarse	:	8μm, 9μm, 12μm, 15μm, 20μm
Rohs requirement	:	Pass
Appearance quality convex	:	No oxidation, Smooth and no concave-convex
Storage requirement	:	Temperature: 25°C, Humidity □≤60 %RH There are no corrosive gas and material, Moist material.
<b>Main Inspect Verifier</b>	:	<b>Manager QC</b>

**Intelligent Materials Pvt. Ltd.**

www.nanoshel.com, sales@nanoshel.com



**Note:** Product Specification are subject to amendment and may change over time



---

**NANOSHEL LLC** *(In Collaboration)*  
3422 Old Capitol Trial Suit 1305, Wilmington DE - 19808 USA  
(001) 302 652-3464, + 91 9779-880077

Characterization of Cu, Purity: >99.8%, APS: 10?m



Copper Foil Sheet Roll



**NANOSHEL**  
Creating Miracles in Black