

Specification Sheet

MWCNT Enabled Quick Drying Enamel

Stock No: NS6130-04-448, CAS: N/A

Product	:	Quick Drying Enamel
Stock No	:	NS6130-04-448
Product Brand	:	Supreme
APS	:	10 nm
Purity	:	>95%
Color	:	Black
Density	:	1.09 Kg/Litre
Viscosity	:	450 - 500 Cpu
Finish	:	Full Gloss
MWCNT	:	2.950 – 3.010 Wt%
Vehicle Type	:	Styrenated Alkyd
Pigment Type	:	Inorganic Oxides & Chromates
Solvent Type	:	Aromatic Hydrocarbons
Flash Point Min	:	22 °C
Drying Time: Surface	:	10 - 15 Minutes
Hard	:	1 - 2 Hours
Application Method	:	Spray Or Dip
Application Viscosity	:	Conventional Spray: 18 – 20” Fc4
Recommended Thinner	:	Q.D Enamel Thinners
Fineness of Grind	:	5 Microns
Gloss	:	85% On 60°
Heat Resistance	:	250 - 300 Degrees C
Coverage At Dft 40 µm	:	8 Square Metres Per Litre
Dry Film Thickness	:	40 Microns (Recommended)
Shelf Life	:	6 - 12 Months
Storage	:	Store Away From Direct Heat
Main Inspect Verifier	:	Manager QC

NANOSHEL LLC (In Collaboration)

3422 Old Capitol Trial Suit 1305, Wilmington DE - 19808 USA
(001) 302 652-3464, + 91 9779-880077

Note: Product Specification are subject to amendment and may change over time

