

# Specification Sheet

## EVA Foam Sheet

(Ethylene Vinyl Acetate blended copolymers)

Stock No: NS6130-10-1266, CAS: 24937-78-8

<b>Product</b>	:	<b>EVA Foam Sheet</b>
Stock No	:	NS6130-10-1266
CAS	:	24937-78-8
Purity	:	>99.9%
Density	:	30 kg/m <sup>3</sup>
Thermal Conductivity	:	0.038 W/mK
Compressive Strength	:	78 Kpa
Surface Hardness	:	40 °C
Tear Strength	:	0.35 N/mm m <sup>2</sup>
Tensile Strength	:	780 Kpa
Elongation at break	:	100 %
Compression deformation	:	25 %
Size Change Rate	:	0.8 %
Rebound Rate	:	26.00 %
Elongation	:	130 %
Service Temperature	:	-30 to 180 °F
Adhesive Thickness	:	0.15 mm
Adhesive Weight	:	80 g/m <sup>3</sup>
Adhesion	:	18 N/25 mm
Application	:	+10 °C min
Service	:	-50~+100 °C
Short peak	:	+120 °C
Storage	:	3 year
Conclusion	:	The specifications Confirm with enterprise standard
<b>Main Inspect Verifier</b>	:	<b>Manager QC</b>

**NANOSHEL LLC** (In Collaboration)

3422 Old Capitol Trial Suit 1305, Wilmington DE - 19808 USA  
(001) 302 652-3464, + 91 9779-880077

**Note:** Product Specification are subject to amendment and may change over time



## Characterization of EVA Foam Sheet



EVA Foam Sheet

